

Title	Investigation on thermal fatigue
Sub Title	
Author	金沢, 健二(Kanazawa, Kenji)
Publisher	慶應義塾大学藤原記念工学部
Publication year	1966
Jtitle	Proceedings of the Fujihara Memorial Faculty of Engineering Keio University (慶應義塾大学藤原記念工学部研究報告). Vol.19, No.76 (1966.) ,p.224(6)- 224(6)
JaLC DOI	
Abstract	
Notes	Summaries of Doctor and Master Theses Master of Engineering, 1966
Genre	Departmental Bulletin Paper
URL	https://koara.lib.keio.ac.jp/xoonips/modules/xoonips/detail.php?koara_id=KO50001004-00190076-0006

慶應義塾大学学術情報リポジトリ(KOARA)に掲載されているコンテンツの著作権は、それぞれの著作者、学会または出版社/発行者に帰属し、その権利は著作権法によって保護されています。引用にあたっては、著作権法を遵守してご利用ください。

The copyrights of content available on the KeiO Associated Repository of Academic resources (KOARA) belong to the respective authors, academic societies, or publishers/issuers, and these rights are protected by the Japanese Copyright Act. When quoting the content, please follow the Japanese copyright act.

Investigation on Thermal Fatigue

Kenji KANAZAWA*

Thermal fatigue is not only important practically, but also very interesting scientifically, and many investigators have so far studied on this problem.

This paper will report about the mechanical and temperature factors which are mainly controlling thermal fatigue fracture.

For the purpose of knowing mechanical and thermal influences on the fatigue fracture, the author made various experiments on thermal fatigue tests, changing the constraint conditions at various temperature conditions.

As a results, it was found that under the same temperature conditions the relation between plastic strain range ($\Delta \varepsilon_p$) and number of cycles (N_c) to macroscopic crack does not always independent to stress ranges ($\Delta \sigma$). Though the strain energy per cycle which is related to $\Delta \sigma$ and $\Delta \varepsilon_p$ has been used by some investigators, the author's experiment resulted in the fact that even if strain energy per cycle is the same, N_c depends remarkably upon temperature conditions. Therefore, as an attempt, the author normalizes the temperature dependence of strain energy contributing to fatigue failure by using the following relation

$$\delta U^* = C'(T, t) \delta U$$

and re-arranges the original experimental data through the effective energy per cycle represented by the following equation

$$U^* = A \int_T e^{-\frac{C}{T} \sigma} \frac{d\varepsilon(T)}{dT} dT$$

Thus, an interesting result was obtained, that for the same U^* the macroscopic crack initiates under same numbers of cycles, independent on temperature conditions.

For 18-8- T_i stainless steel used in present experiments the following relation between U^* and N_c was held ;

$$(U^*/A) N_c^{0.49} = 3.31 \times 10^{-2}$$
$$U^* : \text{Kgmm/mm}^3$$

*金 沢 健 二